

Hole ID	from	to	int	Cr2O3%	Cr%	Fe%	Cr:Fe	N%	Pt g/t	Pd g/t	Au g/t	TPM g/t
<b>NOT-09-1G101</b>	138.1	140.8	2.7	31.32	21.43	16.67	1.29	0.12	0.12	0.13	0.19	0.43
then	179.5	182.8	3.3	19.94	13.63	10.34	1.32	0.21	0.15	<b>0.39</b>	0.04	0.57
then	213.3	223.4	10.0	10.86	7.45	9.90	0.75	0.19	0.12	<b>0.30</b>	0.03	0.45
then	237.4	237.8	0.4	33.43	22.99	14.00	1.64	0.18	0.14	0.17	0.02	0.34
then	252.9	253.5	0.6	27.12	18.50	14.90	1.24	0.12	0.11	0.16	0.02	0.29
then	276.0	292.3	16.3	28.39	19.42	11.05	<b>1.76</b>	0.17	0.11	0.14	0.02	0.27
including	276.0	282.2	6.1	21.92	14.99	9.91	1.51	0.18	0.14	0.19	0.02	0.35
followed by	282.2	291.3	9.2	33.85	23.15	11.96	<b>1.94</b>	0.16	0.09	0.12	0.03	0.23
followed by	291.3	292.3	1.0	18.01	12.30	9.63	1.28	0.12	0.07	0.07	0.01	0.15
then	325.4	326.5	1.1	0.79	0.53	11.00	0.05	<b>0.79</b>	0.07	0.24	0.13	0.44
then	416.2	440.5	24.3	17.61	12.05	10.01	1.20	0.19	0.12	<b>0.25</b>	0.02	0.39
including	416.2	437.3	21.1	15.96	10.92	9.89	1.10	0.18	0.13	<b>0.26</b>	0.02	0.40
then	437.3	439.4	2.1	37.49	25.64	12.14	<b>2.11</b>	0.17	0.16	<b>0.25</b>	0.03	0.43

<b>NOT-09-1G102</b>	404.0	410.9	6.9	5.77	3.94	9.74	0.41	0.13	0.04	0.08	0.01	0.13
---------------------	-------	-------	-----	------	------	------	------	------	------	------	------	------

<b>NOT-09-1G104</b>	61.9	66.4	4.5	16.10	11.01	10.85	1.01	0.19	0.11	0.20	0.09	0.40
then	118.6	142.8	24.2	17.15	11.73	10.27	1.14	0.18	0.10	0.20	0.03	0.34
including	118.6	137.6	19.0	12.73	8.71	9.56	0.91	0.19	0.10	0.20	0.04	0.33
followed by	137.6	141.8	4.2	37.96	25.97	13.86	<b>1.87</b>	0.13	0.14	0.24	0.02	0.40
followed by	141.8	142.8	0.9	14.09	9.64	8.88	1.09	0.22	0.07	0.15	0.00	0.23
then	159.0	166.4	7.4	13.04	15.02	16.29	0.92	0.19	0.15	<b>0.36</b>	0.05	0.56
including	159.0	163.4	4.4	17.96	12.28	15.95	0.77	0.16	0.13	<b>0.29</b>	0.03	0.44
followed by	163.4	165.3	1.9	7.99	5.46	22.32	0.24	<b>0.26</b>	<b>0.26</b>	<b>0.64</b>	0.11	1.01
then	224.9	252.4	27.6	15.88	10.86	9.12	1.19	0.13	0.08	0.09	0.02	0.20
followed by	224.9	247.8	22.9	13.89	9.50	8.67	1.10	0.13	0.07	0.08	0.01	0.16
followed by	247.8	252.4	4.7	25.59	17.51	11.33	<b>1.54</b>	0.16	0.13	0.14	0.09	0.36
then	289.5	290.2	0.7	13.34	9.13	11.32	0.81	0.13	0.07	0.10	0.04	0.21
then	303.8	410.8	106.9	22.53	15.41	10.41	1.48	0.16	0.11	0.18	0.01	0.29
including	303.8	318.4	14.5	25.19	17.23	11.65	1.48	0.24	0.21	<b>0.47</b>	0.01	0.69
followed by	318.4	343.4	25.1	36.82	25.19	12.46	<b>2.02</b>	0.16	0.13	0.19	0.01	0.33
highlighted by	324.4	329.7	5.2	40.61	27.78	13.17	<b>2.11</b>	0.14	0.10	0.08	0.00	0.19
followed by	343.4	379.7	36.2	13.83	9.46	9.03	1.05	0.14	0.10	0.12	0.00	0.22
followed by	379.7	385.0	5.4	34.63	23.70	13.47	<b>1.76</b>	0.15	0.13	0.17	0.00	0.30
followed by	385.0	410.8	25.8	16.84	11.52	9.02	1.28	0.13	0.09	0.12	0.08	0.29

<b>NOT-09-1G109</b>	37.3	37.5	0.2	16.08	11.00	13.30	0.83	0.11	<b>0.25</b>	<b>0.31</b>	0.00	0.57
then	102.7	106.6	4.0	0.00	0.00	0.00	na	<b>0.70</b>	0.05	<b>0.31</b>	0.01	0.37

<b>NOT-09-1G110</b>	55.6	57.2	1.5	29.41	20.12	13.67	1.47	0.12	0.14	0.11	0.00	0.25
then	59.7	95.3	35.6	36.54	24.99	13.75	<b>1.82</b>	0.12	0.15	0.16	0.01	0.31
including	59.7	70.1	10.4	36.29	24.82	15.29	<b>1.62</b>	0.12	0.14	0.13	0.00	0.27
followed by	70.1	72.8	2.7	41.08	28.10	14.75	<b>1.91</b>	0.10	0.12	0.12	0.01	0.25
followed by	72.8	76.9	4.1	32.63	22.32	13.25	<b>1.68</b>	0.10	0.11	0.06	0.00	0.17
followed by	76.9	81.4	4.6	42.37	28.98	13.43	<b>2.16</b>	0.13	0.15	0.12	0.00	0.27
followed by	81.4	95.3	13.8	35.06	23.97	12.65	<b>1.89</b>	0.13	0.16	0.22	0.01	0.40

<b>NOT-09-1G112</b>	36.5	39.8	3.3	22.78	15.58	12.30	1.27	0.12	0.10	0.10	0.01	0.21
then	81.3	87.6	6.3	37.81	25.86	12.22	<b>2.12</b>	0.13	0.22	0.23	0.00	0.45
including	81.3	81.8	0.5	14.22	9.73	8.10	1.20	0.16	0.20	0.22	0.00	0.42
followed by	81.8	87.6	5.8	39.91	27.30	12.59	<b>2.17</b>	0.12	0.22	0.23	0.00	0.45
followed by	90.3	96.6	6.3	35.67	24.40	13.86	<b>1.76</b>	0.12	0.16	0.19	0.00	0.36
then	225.8	227.5	1.6	35.50	24.28	14.46	<b>1.68</b>	0.12	0.15	0.20	0.00	0.36
then	233.1	233.4	0.3	24.27	16.60	16.80	0.99	0.14	<b>0.29</b>	<b>0.47</b>	0.01	0.77

<b>NOT-09-1G114</b>	21.3	24.1	2.75	11.86	8.12	8.79	0.92	0.15	0.06	0.05	0.00	0.11
---------------------	------	------	------	-------	------	------	------	------	------	------	------	------

<b>NOT-09-1G117</b>	63.5	76.3	12.8	0.00	0.00	0.00	NA	0.13	0.03	0.09	0.61	0.73
then	112.0	121.0	9.0	0.00	0.00	0.00	NA	<b>0.92</b>	0.19	<b>0.44</b>	0.04	0.67

<b>NOT-09-1G118</b>	71.4	76.3	4.9	15.24	10.42	8.97	1.16	0.14	0.08	0.17	0.02	0.26
then	96.0	114.4	18.4	30.44	20.82	11.04	<b>1.89</b>	0.15	0.12	0.14	0.04	0.30
including	96.0	105.0	9.0	36.13	24.72	11.51	<b>2.15</b>	0.14	0.13	0.13	0.03	0.28
followed by	105.0	108.9	3.9	40.17	27.47	13.13	<b>2.09</b>	0.15	0.14	0.15	0.02	0.30
followed by	108.9	114.4	5.5	14.36	9.82	8.81	1.11	0.17	0.10	0.15	0.08	0.33
then	144.7	146.6	1.9	12.14	8.31	12.86	0.65	0.13	<b>0.25</b>	<b>0.46</b>	0.13	0.84
then	155.8	157.0	1.2	36.40	24.90	19.20	1.30	0.21	<b>0.31</b>	<b>0.58</b>	<b>0.45</b>	<b>1.33</b>
then	187.0	189.4	2.3	21.91	15.00	13.66	1.10	0.18	0.10	0.14	0.08	0.31
then	206.3	212.0	5.7	20.53	14.04	12.40	1.13	0.17	0.12	<b>0.31</b>	0.14	0.56
then	222.5	232.5	10.0	12.95	8.86	10.88	0.81	0.14	0.07	0.07	0.02	0.17
then	232.5	234.0	1.5	5.43	3.72	10.60	0.35	<b>0.30</b>	0.06	0.08	0.22	0.36

<b>NOT-09-1G119</b>	122.0	135.3	13.3	0.00	0.00	0.00	NA	<b>0.54</b>	0.06	0.17	0.02	0.26
including	122.0	133.5	11.5	0.00	0.00	0.00	NA	<b>0.42</b>	0.06	0.14	0.02	0.21
followed by	133.5	135.3	1.8	0.00	0.00	0.00	NA	<b>1.33</b>	0.11	<b>0.39</b>	0.06	0.56

<b>NOT-09-1G130</b>	27.0	60.9	33.9	31.85	21.79	11.50	<b>1.89</b>	0.15	0.17	0.16	0.00	0.33
including	27.0	37.1	10.1	10.78	7.37	6.93	1.06	0.16	0.05	0.06	0.00	0.11
followed by	37.1	58.6	21.5	41.58	28.45	13.33	<b>2.13</b>	0.14	0.20	0.14	0.00	0.35
followed by	58.6	60.9	2.3	0.55	0.38	4.65	0.081	0.18	<b>0.36</b>	<b>0.79</b>	0.01	<b>1.17</b>
then	167.2	168.5	1.3	0.00	0.00	0.00	NA	<b>1.27</b>	<b>0.53</b>	<b>2.69</b>	0.05	<b>3.27</b>

<b>NOT-09-1G131</b>	36.6	39.1	2.6	33.25	22.75	15.58	1.46	0.13	0.22	<b>0.35</b>	0.01	0.59
---------------------	------	------	-----	-------	-------	-------	------	------	------	-------------	------	------

**HIGHLIGHTS (those with Cr:Fe > 2.0)**

Hole Number	from (m)	to (m)	int (m)	Cr2O3%	Cr%	Fe%	Cr:Fe
<b>NOT-09-1G101</b>	437.3	439.4	2.1	37.49	25.64	12.14	2.11
<b>NOT-09-1G104</b>	318.4	343.4	25.1	36.82	25.19	12.46	2.02
including	324.4	329.7	5.2	40.61	27.78	13.17	2.11
<b>NOT-09-1G110</b>	76.9	81.4	4.6	42.37	28.98	13.43	2.16
<b>NOT-09-1G112</b>	81.3	87.6	6.3	37.81	25.86	12.22	2.12
<b>NOT-09-1G118</b>	96.0	105.0	9.0	36.13	24.72	11.51	2.15
followed by	105.0	108.9	3.9	40.17	27.47	13.13	2.09
<b>NOT-09-1G130</b>	37.1	58.6	21.5	41.58	28.45	13.33	2.13